

In the Claims:

Please amend the Claims as follows:

Please cancel Claims 10 and 11 without prejudice.

Claim 1 (Previously amended): A two-ply polyurethane geotextile composite in which a dimensionally stable geotextile is bonded to a pliable geotextile with a solidifiable liquid polyurethane composition which is a reaction product of a mixture comprising:

- B
- a) a liquid polyisocyanate having an isocyanate content of at least 10% by weight,
 - b) an isocyanate reactive component comprising a polyether polyol having from 2 to 6 hydroxyl groups and a number average molecular weight of from 250 to 8,000 and 0 to 10% by weight, based on total weight of b), of a low molecular weight diol or triol having an equivalent weight of from 31 to 99,
 - c) a urethane catalyst, and optionally,
 - d) a filler.

Claim 2 (Original): The composite of Claim 1, wherein the polyether polyol b) comprises a polyoxypropylene polyether having a number average molecular weight of from about 400 to about 4,000 and an average functionality of 2 to 3.

Claim 3 (Original): The composite of Claim 1, wherein the polyether polyol b) comprises:

- (i) from about 5 to about 15 parts by weight of a propylene oxide adduct of an alkanolamine which adduct has a number average molecular weight of from 250 to about 1000,
- (ii) a propylene oxide adduct of a low molecular weight organic compound having from about 3 to about 6 OH groups which adduct has a number average molecular weight of from 250 to 1000, and
- (iii) a propylene oxide adduct of a low molecular weight diol which adduct has a number average molecular weight of from 250 to about 3000.

Mo5942

- 2 -

BEST AVAILABLE COPY

Claim 4 (Original): The composite of Claim 1, wherein the catalyst c) comprises an organic tin compound.

Claim 5 (Original): The composite of Claim 1, wherein the liquid polyisocyanate a) is an aromatic polyisocyanate.

Claim 6 (Original): The composite of Claim 1, wherein the liquid polyisocyanate a) is a polymethylene poly(phenylisocyanate) having an NCO-content of about 30 to 33% and a viscosity of about 20 mPa·s to 2,000 mPa·s at 25°C.

B¹
Claim 7 (Previously amended): The composite of Claim 1, wherein the dimensionally stable geotextile has a maximum thickness of 1 mm.

Claim 8 (Previously amended): The composite of Claim 1, wherein the pliable geotextile has a minimum thickness of 1 mm.

Claim 9 (Previously amended): The composite of Claim 1, wherein the pliable geotextile has at least one side burnished.

Claims 10 and 11 (Cancelled)

Claims 12-27 (Withdrawn)

Mo5942

- 3 -